

Purolite® NRW3240

Polystyrenic Gel Gel Mixed Bed
Resin Hydrogen form Hydroxide
Form, Nuclear Grade

PRINCIPAL APPLICATIONS

- Primary coolant polishing

SYSTEMS

- Clean-up systems

TYPICAL PACKAGING

- 1 CF Box
- 5 CF Drum (Fiber)
- 25 L Sack - Heat sealed

TYPICAL PHYSICAL & CHEMICAL CHARACTERISTICS:

Appearance	Spherical Beads	
Particle Size Range	425 - 1200 µm	
Uniformity Coefficient (max.)	1.7	
Impurities Iron (max.)	50 ppm	
Impurities Sodium (max.)	30 ppm	
Impurities Heavy Metals (max.)	40 ppm	
Anionic Form, CO ₃ ²⁻ (max.)	5 %	
Anionic Form, SO ₄ ²⁻ (max.)	0.1 %	
Anionic Form, Cl ⁻ (max.)	0.1 %	
Shipping Weight (approx.)	705 - 740 g/L (44.1 - 46.2 lb/ft ³)	
Temperature Limit, Non-Regenerable Bed	100 °C (212.0 °F)	
Temperature Limit, Regenerable Bed	60 °C (140.0 °F)	
Component Name	Gel Strong Acid Cation	Gel Strong Base Anion
Polymer Structure	Gel polystyrene crosslinked with divinylbenzene	Gel polystyrene crosslinked with divinylbenzene
Functional Group	Sulfonic Acid	Type I Quaternary Ammonium
Ionic Form	H ⁺	OH ⁻
Cation / Anion Chemical Equivalent Ratio	1	1
Total Capacity (min.)	1.8 eq/L (H ⁺ form)	1 eq/L (OH ⁻ form)
Conversion (min.)	99.9 % (H ⁺ form)	95 % (OH ⁻ form)



Americas
T +1 610 668 9090
F +1 610 668 8139
americas@purolite.com

Europe
T +44 1443 229334
F +44 1443 227073
europe@purolite.com

Asia Pacific
T +86 571 876 31382
F +86 571 876 31385
asiapacific@purolite.com



Americas
T +1 610 668 9090
F +1 610 668 8139
americas@purolite.com

Europe
T +44 1443 229334
F +44 1443 227073
europe@purolite.com

Asia Pacific
T +86 571 876 31382
F +86 571 876 31385
asiapacific@purolite.com